

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 September 2003 (12.09.2003)

PCT

(10) International Publication Number
WO 03/074619 A1

(51) International Patent Classification⁷: C09D 11/10, B41J 11/00, B41M 7/00, 5/40, B05D 7/00, B41J 2/21

(74) Agent: ELKINGTON AND FIFE; Prospect House, 8
Pembroke Road, Sevenscaks, Kent TN13 1XR (GB).

(21) International Application Number: PCT/GB03/00832

(22) International Filing Date: 27 February 2003 (27.02.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0205151.4 5 March 2002 (05.03.2002) GB

(71) Applicant (for all designated States except US): DOTRIX
NV [BE/BE]; Tramstraat 69, B-9052 Gent (BE).

(71) Applicant (for GB only): SERICOL LIMITED
[GB/GB]; Patricia Way, Pysons Road Industrial Es-
tate, Broadstairs, Kent CT10 2LE (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): DECKERS,
Bernard [BE/BE]; Pedestraat 67b, B-1602 Vlezenbeek
(BE). NIXON, Keith, Edward [GB/GB]; 12 Ranelagh
Road, 41 Edge End Road, Broadstairs, Kent CT10 2AH
(GB).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE,
SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI,
SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: INK-JET PRINTING PROCESS AND INK-JET INKS USED THEREIN

(57) Abstract: The present invention relates to an improved process for wet-on-wet ink-jet printing. This invention provides a progressive dot printing ink-jet process comprising the steps of applying a first ink drop to a substrate and subsequently applying a second ink drop on to the first ink drop without intermediate solidification of the first ink drop. The first and second ink drops have a different viscosity, surface tension or curing speed. Further ink drops may be applied sequentially to the combined first and second ink drops without intermediate solidification of the first and subsequent ink drops.

WO 03/074619 A1

INK-JET PRINTING PROCESS AND INK-JET INKS USED THEREIN

The present invention relates to an ink-jet ink printing process and in particular to the provision of an improved process for wet-on-wet ink-jet printing.

5

In ink-jet printing, minute droplets of ink are ejected in a controlled manner from one or more reservoirs or printing heads through nozzles onto a substrate, which is moving relative to the reservoirs. The ejected ink forms an image on the substrate. For high-speed printing, the inks must flow rapidly from the printing heads and this puts a number of constraints on the physical properties of the ink. These constraints include a low viscosity which for piezoelectric Drop-on-Demand (DOD) ink-jet printing is usually 1-50 mPas, preferably 6-30 mPas, particularly preferably 8-15 mPas (at the jetting temperature which may be from 25 to 110°C.), and a surface tension such that the jet can form the necessary small droplets (10-50 dyne/cm, preferably 25-35 dyne/cm). The ink must also be a homogenous liquid capable of rapid conversion to a dry printed area. The particles of pigment dispersed therein should have a particle size of less than 8 μm , preferably less than 3 μm and particularly preferably less than 1 μm .

20

The concept of piezoelectric ink-jet printing is based on the movement of a piezoelectric ceramic transducer when a voltage is applied thereto. When the voltage is applied, the shape of the ceramic changes, creating a void, which is filled with ink. When the voltage is then removed, the ceramic expands to its original shape, ejecting a drop of ink from the print head.

25

The printing system generally used is a flexible single pass unit with piezoelectric heads. One ink drop can therefore be printed onto another without intermediate solidification of the first ink drop. This is known as wet-on-wet printing. The phrase "without intermediate solidification" is understood in the art to mean that the first or subsequent ink drop is still liquid when the next ink drop is applied. In order to avoid curing the first or subsequent ink drops before the next ink drop is applied, the first or subsequent ink drops are not cured, i.e. they are not irradiated prior to application of the next ink drop.

30

Wet-on-wet printing is primarily used in colour printing to apply ink drops of differing colours sequentially to the same area of the substrate which then combine to produce the desired colour. The typical four-colour set is Cyan, Magenta, Yellow, and Black known
5 as C-M-Y-K but the technique is extendable to six-colour hexachrome or any progressive dot printing ink-jet process. The inks used are known 100% solids UV pigmented inks.

Good print definition quality requires the following: a rapid formation of a solid coloured dot from the ink composition; concentration of the ink colourants on the surface of the
10 substrate without being absorbed into the substrate surface; control of the spread of the dot of colour formed on the surface of the substrate; limited merging or bleed of the ink of one colour from a dot to a neighbouring dot of a different colour; and uniformity of colour and colour density over the solid area of print formed from the droplets.

15 The most common problems associated with wet-on-wet printing are mottling, puddling and the lack of sharp lines. Mottling and puddling are related to the printing of solid areas when the colour density varies across the area of print. The sharpness of line edges is important in achieving clear images in, for example, text.

20 Accordingly, the present invention provides a progressive dot printing ink-jet process comprising the steps of applying a first ink drop to a substrate and subsequently applying a second ink drop on to the first ink drop without intermediate solidification of the first ink drop, wherein the first and second ink drops have a different viscosity, surface tension or curing speed.

25

Preferably, further ink drops are applied sequentially to the first and second ink drops without intermediate solidification of the combined first and subsequent ink drops.

Preferably, at least four ink drops are applied sequentially.

30

Preferably, the first and subsequent ink drops are different colours.

Preferably, the ink drops are cyan, magenta, yellow and black.

Preferably, the viscosity of the first and last ink drops applied varies in a graduated
5 manner within a range of from 10 up to 30 mPas or 30 down to 10 mPas.

Preferably, the surface tension of the first and last ink drops applied varies in a graduated
manner within a range of from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm.

10 Preferably, the cure speed of the first and last ink drops applied varies in a graduated
manner within a range of from 20 up to 70 m/min or 70 down to 20 m/min.

In another embodiment, the present invention also provides a set of ink-jet inks suitable
for use in a progressive dot printing ink-jet process comprising at least two inks having a
15 different viscosity, surface tension or curing speed.

In a further embodiment, the present invention also provides an ink dispenser holding a
set of ink-jet inks.

20 The ink compositions of the present invention include at least three main components.
These are (i) monomers and/or oligomers, (ii) photoinitiators, and (iii) colourant(s),
preferably a pigment. In addition, the inks may, optionally, contain surfactant and
synergist additives.

25 Monomers, oligomers or prepolymers may possess different degrees of functionality, and
a mixture including combinations of mono-, di-, tri- and higher functionality monomers,
oligomers or prepolymers may be used. These components are curable, typically
photocurable, e.g. UV curable, and should adhere to the substrate surface after printing
and serve to bind the pigment. Also adjusting the ratio of the monomers or oligomers is a
30 method of adjusting the viscosity of the ink. To obtain a gradient of viscosity the ratio
between monomers and oligomers is modified. A higher functionality results in a higher

viscosity. The viscosity varies in graduations from the most viscous ink to the least viscous ink or vice versa. Preferably, the viscosity varies from 10 up to 30 mPas or 30 down to 10 mPas, particularly preferably from 12 up to 22 mPas or 22 down to 12 mPas. The viscosity is measured using standard techniques known in the art.

5

Additionally, improvements in print quality may be achieved using a gradient of surface tension across the progressive colours (e.g. C-M-Y-K). To obtain a gradient of surface tension the ratio of monomers, oligomers or prepolymers is modified and also surfactant additives are used to lower the surface tension. Preferably, the surface tension varies from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm. Particularly preferably from 22 up to 31 dynes/cm or 31 down to 22 dynes/cm. The surface tension is measured using standard techniques known in the art.

10

Furthermore, improvements in print quality are achieved using a gradient of cure speeds across the progressive colours (e.g. C-M-Y-K). To obtain a gradient in cure speeds the initiators and synergist additives are modified. Preferably, the cure speed varies from 20 up to 70 meters (m)/min or 70 down to 20 m/min. Particularly preferably from 30 up to 50 m/min or 50 down to 30 m/min. Measurements are made on a 12 μ m film of ink coated onto rigid PVC and passed under a 120 W/cm medium pressure mercury lamp.

15

20

Although the viscosity, surface tension or cure speed of the first and subsequent drops may vary in graduations from low to high or high to low, it is preferred that the first and subsequent drops increase in viscosity, i.e. that the first and subsequent drops vary in graduations from least viscous to most viscous, and that the surface tension of the drops and the cure speed decreases from the first to the last ink printed, i.e. from highest surface tension to lowest surface tension and from highest cure speed to lowest cure speed.

25

The monomers, oligomers or prepolymers (i) are typically monofunctional and/or polyfunctional acrylate monomers, oligomers or prepolymers, such as an ester of acrylic or methacrylic acid, such as octyl acrylate, decyl acrylate, hydroxyethyl methacrylate lauryl acrylate, phenoxyethyl acrylate, hexanediol diacrylate, polyethylene glycol

30

diacrylate, tri(propylene glycol) triacrylate, trimethylolpropane triacrylate, bis(pentaerythritol) hexa-acrylate; or an N-vinylamide such as, N-vinylcaprolactam or N-vinylformamide; or acrylamide or a substituted acrylamide, such as acryloylmorpholine. Preferred monomers, oligomers or prepolymers are the acrylate esters of the ethoxylated or propoxylated derivatives of di-, tri- or tetrahydric aliphatic alcohols, and the acrylate or methacrylate esters of epoxy, urethane, melamine or polyester resins or their ethoxylated or propoxylated derivatives.

These components may be sold under the names: Ebecryl 40, Ebecryl 1039, DPGDA, TPGDA, ODA-n, TTEGDA, Ebecryl 160, OTA 480, IRR 289, TMPTA, IRR 184, Ebecryl 111, Ebecryl 110, IBOA, HDDA, Ebecryl 81, ACTILANE 872, ACTILANE 735, ACTILANE 584, ACTILANE 525, ACTILANE 440, ACTILANE 432, ACTILANE 430, ACTILANE 423, ACTILANE 421 and ACTILANE 251.

The term "monofunctional" means one reactive functional group, e.g. acrylate, per monomer or oligomer and includes IBOA, Ebecryl 110, ODA-N and Ebecryl 1039. The term "polyfunctional" means more than one reactive functional group, e.g. acrylate, per monomer or oligomer and includes HDDA, DPGDA, TPGDA, TTEGDA, TMPTA and OTA 480.

Photoinitiators (ii) are necessary for free radical curing and may include, but are not limited to, the following compounds or combinations thereof: benzophenone and substituted benzophenones, 1-hydroxycyclohexyl phenyl ketone, thioxanthenes such as isopropylthioxanthone, 2-hydroxy-2-methyl-1-phenylpropan-1-one, 2-benzyl-2-dimethylamino-(4-morpholinophenyl)butan-1-one, benzil dimethylketal, bis(2,6-dimethylbenzoyl)-2,4,4-trimethylpentylphosphine oxide, 2,4,6-trimethylbenzoyldiphenylphosphine oxide, 2-methyl-1-[4-(methylthio)phenyl]-2-morpholinopropan-1-one, 2,2-dimethoxy-1,2-diphenylethan-1-one or 5,7-diiodo-3-butoxy-6-fluorone. Other useful photoinitiators are the so-called "cationic" type, which liberate a diffusible strong acid on exposure to ultra-violet light. Examples include

iodonium and sulfonium salts, such as diphenyliodonium fluoride and triphenylsulfonium hexafluorophosphate.

These may be sold under the Trade names of Irgacure 184, Irgacure 500, Darocure 1173,
5 Irgacure 907, ITX, Lucerin TPO, Irgacure 369, Irgacure 1700, Darocure 4265, Irgacure
651, Irgacure 819, Irgacure 1000, Irgacure 1300, Esacure KT046, Esacure KIP150,
Esacure KT37, Esacure EDB, H-Nu 470 and H-Nu 470X.

Colourants (iii) may be suitable dyes or preferably pigments selected for colour,
10 dispersion or the other reasons. Colourants are well known in the art and include, but are
not limited to those within the ranges having the following CI classifications: Green PG 7
and 36; Orange PO 5, 34, 36, 38, 43, 51, 60, 62, 64, 66, 67 and 73; Red PR 112, 149, 170,
178, 179, 185, 187, 188, 207, 208, 214, 220, 224, 242, 251, 254, 255, 260 and 264;
Magenta/Violet PV 19, 23, 31 and 37 and PR 122, 181 and 202; Yellow PY 17, 120, 138,
15 155, 168, 175, 179, 180, 181 and 185; Blue PB 15; Black PB 2, 5 and 7. Examples of
specific pigments include IRGALITE BLUE GLVO, MONASTRAL BLUE FGX,
IRGALITE BLUE GLSM, HELIOGEN BLUE L7101F, LUTETIACYANINE ENJ,
HELIOGENBLUE L6700F, MONASTRAL GNXC, MONASTRAL GBX,
MONASTRAL GLX MONASTRAL 6Y, IRGZIN DPP ORANGE RA, NOVAPERM
20 ORANGE H5G70, NOVPERM ORANGE HL, MONOLITE ORANGE 2R,
NOVAPERM RED HFG, HOSTAPERM ORANGE HGL, PALIOGEN ORANGE
L2640, SICOFASST ORANGE 2953, IRGAZIN ORANGE 3GL, CHROMOPHTHAL
ORANGE GP, HOSTAPERM ORANGE GR PV CARMINI HF4C, NOVAPERM RED
F3RK 70, MONOLITE RED BR, IRGAZIN DPP RUBINE TR, IRGAZIN DPP
25 SCARLET EK, RT-390-D SCARLET, RT-280-D RED, NOVAPERM RED HF4B,
NOVAPERM RED HF3S, NOVAPERM RED HF2B, VYNAMON RED 3BFW,
CHROMOPHTHAL RED G, VYNAMON SCARLET 3Y, PALIOGEN RED L3585,
NOVAPERM RED BL, PALIOGEN RED 3880 HD, HOSTAPERM P2GL,
HOSAPERM RED P3GL, HOSTAPERM RED E5B 02, SICOFASST RED L3550,
30 SUNFAST MAGENTA 122, SUNFAST RED 122, SUNFAST VIOLET 19 228-0594,
SUNFAST VIOLET 19 228-1220, CINQUASIA VIOLET RT-791-D, VIOLET R NRT-

201-D, RED B NRT-796-D, VIOLET R RT-101-D, MONOLITE VIOLET 31,
 SUNFAST MAGENTA 22, MAGENTA RT-243-D, MAGENTA RT 355-D, RED B RT-
 195-D, CINQUASIA CARBERNET RT-385-D, MONOLITE VIOLET R, MICROSOL
 VIOLET R, CHROMOPHTHAL VIOLET B, ORACET PINK RF, IRGALITE YELLOW
 5 2GP, IRGALITE YELLOW WGP, PV FAST YELLOW HG, PV FAST YELLOW H3R,
 HOSTAPERM YELLOW H6G, PV FAST YELLOW, PALIOTOL YELLOW D1155
 AND IRGZIN YELLOW 3R.

Synergist additives may be used to improve the curing quality and to diminish the
 10 influence of the oxygen inhibition. Such additives include, but are not limited to
 ACTILANE 800, Ebecryl P115, Ebecryl 350, ACTILANE 725, CD 1012 and DIDMA.

Surfactant additives are used primary to modify the surface tension of the inks. Such
 additives include, but are not limited to ACTILANE 800, Tego glide 410, Tego glide
 15 435, Tego glide 440, Tego glide 450, Tego flow 300, Tego flow 425, Tego flow ZFS460,
 Tego rad 2100, Tego rad 2200 -N, Tego rad 2600, Tego rad 2700, Tego wet ZFS453,
 Tego wet 250, Dow corning 67, SR 492, SR 9003, Surfadone 300, BYK 306, FC-430,
 Fc-171, FC-431, Tego disperse 610, Tego disperse 710, anti terra-u, Disperbyk 108, anti
 terra 204, EFKA 47 and EFKA 400.

20

Examples

In order to exemplify the present invention the following formulation was used:

25	Monofunctional acrylate	15 – 45 %
	Polyfunctional acrylate	45 – 55 %
	Photoinitiators	1.0 – 6.0 %
	Amine acrylate (Synergist additive)	< 5%
	Pigment dispersion	< 3%
30	Tegorad 2100 (Surfactant additive)	0.01-2.0%

Wet-on-wet printing was carried out using a Barco ink-jet (Dot factory) printer on a substrate of self-adhesive PVC foil.

5 Example 1

Inks having a gradient of viscosity of between 12 and 22 mPas across the colours C-M-Y-K were prepared and tested using wet-on-wet printing according to the printing process outlined above. To achieve the viscosity gradient the monofunctional to polyfunctional ratio was varied from 0.35 to 1.5.

The gradient of viscosity was varied from CYAN to BLACK starting at 12 mPas for CYAN and ending at 22 mPas for BLACK, using the following order for the colours:

15	1) CYAN	12 mPas
	2) MAGENTA	14 mPas
	3) YELLOW	18 mPas
	4) BLACK	22 mPas

20 This gave improved print results compared with inks having the same viscosity. In particular, there was there less mottling and puddling, the lines produced were sharper, and the colour was clearer.

Example 2

25

Inks having a gradient of viscosity of between 22 and 12 mPas across the colours C-M-Y-K were prepared and tested using wet-on-wet printing according to the printing process outlined above. To achieve the viscosity gradient the monofunctional to polyfunctional ratio was varied from 0.35 to 1.5.

30

The gradient of viscosity was varied from CYAN to BLACK starting at 22 mPas for CYAN and ending at 12 mPas for BLACK, using the following order for the colours:

- | | | |
|---|------------|---------|
| | 1) CYAN | 22 mPas |
| 5 | 2) MAGENTA | 18 mPas |
| | 3) YELLOW | 14 mPas |
| | 4) BLACK | 12 mPas |

As in Example 1, this gave improved print results compared with inks having the same viscosity.

Example 3

Inks having a gradient of surface tension across the colours C-M-Y-K were prepared and tested using wet-on-wet printing according to the printing process outlined above. The surface tension ranged between 22 and 31 dynes/cm. The surface tension gradient was achieved by modifying the amount of surfactant additives added in the ink compositions from 0.02% to 0.8%.

A gradient of surface tension starting from CYAN at 22 dynes/cm and ending with BLACK at 31 dynes/cm was tested, using the following order for the colours:

- | | | |
|----|------------|-------------|
| | 1) CYAN | 22 dynes/cm |
| | 2) MAGENTA | 25 dynes/cm |
| 25 | 3) YELLOW | 28 dynes/cm |
| | 4) BLACK | 31 dynes/cm |

As in Example 1, this gave improved print results compared with inks having the same surface tension

Example 4

Inks having a gradient of surface tension starting from CYAN at 31 dynes/cm and ending with BLACK at 22 dynes/cm were also tested.

5

The inks were used in the following order:

- | | | |
|----|------------|-------------|
| | 1) CYAN | 31 dynes/cm |
| | 2) MAGENTA | 28 dynes/cm |
| 10 | 3) YELLOW | 25 dynes/cm |
| | 4) BLACK | 22 dynes/cm |

As in Example 1, this also gave improved print results compared with inks having the same surface tension.

15

Example 5

Inks having a gradient of cure speed over the colours C-M-Y-K were prepared and tested. A range of cure speed between 30 and 50 m/minute were used, when measuring a 12 µm film of ink coated onto rigid PVC and passed under a 120 W/cm. medium pressure UV mercury lamp was used. The cure speed gradient was varied by modifying the amount of photoinitiator and synergist additives. A gradient of speeds starting from CYAN at 30 m/min and ending with BLACK at 50 m/min were tested.

20

25 The inks were used in the following order:

- | | | |
|----|------------|----------|
| | 1) CYAN | 30 m/min |
| | 2) MAGENTA | 37 m/min |
| | 3) YELLOW | 45 m/min |
| 30 | 4) BLACK | 50 m/min |

As in Example 1, this gave improved print results compared with inks having the same cure speeds.

Example 6

5

Inks were prepared having a gradient of cure speed over the colours C-M-Y-K and tested. A range of cure speed between 50 and 30 m/minute were used, when measuring a 12 micron film of ink coated onto rigid PVC and passed under a 120 W/cm. medium pressure UV Mercury lamp was used. The cure speed gradient was prepared by
10 modifying the amount of initiators and synergist additives. A gradient of speeds starting from CYAN at 50 m/min and ending with BLACK at 30 m/min were used.

The inks were used in the following order:

- | | | |
|----|------------|----------|
| 15 | 1) CYAN | 50 m/min |
| | 2) MAGENTA | 43 m/min |
| | 3) YELLOW | 36 m/min |
| | 4) BLACK | 30 m/min |

20 As in Example 1, this gave improved print results compared with inks having the same cure speeds.

Claims

1. A progressive dot printing ink-jet process comprising the steps of applying a first ink drop to a substrate and subsequently applying a second ink drop on to
5 the first ink drop without intermediate solidification of the first ink drop, wherein the first and second ink drops have a different viscosity, surface tension or curing speed.
2. A progressive dot printing ink-jet process as claimed in claim 1, wherein further ink drops are applied sequentially to the combined first and second ink drops without
10 intermediate solidification of the first and subsequent ink drops.
3. A progressive dot printing ink-jet process as claimed in claim 1 or 2, wherein at least four ink drops are applied sequentially.
- 15 4. A progressive dot printing ink-jet process as claimed in any preceding claim, wherein the first and subsequent ink drops are different colours.
5. A progressive dot printing ink-jet process as claimed claim 4, wherein the ink drops are cyan, magenta, yellow and black.
20
6. A progressive dot printing ink-jet process as claimed in any preceding claim, wherein the viscosity of the first and last ink drops applied varies in a graduated manner within a range of from 10 up to 30 mPas or 30 down to 10 mPas.
- 25 7. A progressive dot printing ink-jet process as claimed in any preceding claim, wherein the surface tension of the first and last ink drops applied varies in a graduated manner within a range of from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm.
8. A progressive dot printing ink-jet process as claimed in any preceding claim,
30 wherein the cure speed of the first and last ink drops applied varies in a graduated manner within a range of from 20 up to 70 m/min or 70 down to 20 m/min.

9. A set of ink-jet inks suitable for use in a progressive dot printing ink-jet process comprising at least two inks having a different viscosity, surface tension or curing speed.

5 10. A set of ink-jet inks as claimed in claim 9, wherein the ink-jet inks are cyan, magenta, yellow and black.

10 11. A set of ink-jet inks as claimed in claim 9 or 10, wherein the viscosity of the ink-jet inks varies in a graduated manner within a range of from 10 up to 30 mPas or 30 down to 10 mPas.

12. A set of ink-jet inks as claimed in any of claims 9 to 11, wherein the viscosity of the ink-jet inks varies in a graduated manner within a range of from 20 up to 40 dynes/cm or 40 down to 20 dynes/cm.

15 13. A set of ink-jet inks as claimed in any of claims 9 to 12, wherein the viscosity of the ink-jet inks varies in a graduated manner within a range of from 20 up to 70 m/min or 70 down to 20 m/min.

14. An ink dispenser holding a set of ink-jet inks as claimed in any of claims 9 to 13.

INTERNATIONAL SEARCH REPORT

International Application No.

PC1/GB 03/00832

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D11/10 B41J11/00 B41M7/00 B41M5/40 B05D7/00
B41J2/21

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D B41J B41M B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 145 979 A (CAIGER NIGEL ANTONY ET AL) 14 November 2000 (2000-11-14) column 2, line 25 -column 4, line 29; figure 5	1-5,9, 10,14
X	WO 00 30856 A (XAAR TECH LTD ;TEMPLE STEPHEN (GB)) 2 June 2000 (2000-06-02) page 2, line 2 -page 5, line 24	1-5,9, 10,14
X	US 2001/038408 A1 (QUATTROCIOCCHI ANGELO ET AL) 8 November 2001 (2001-11-08) paragraph '0019! - paragraph '0036!; figure 1	1-5,9, 10,14
A	EP 0 914 875 A (KANSAI PAINT CO LTD) 12 May 1999 (1999-05-12) page 9, line 23 -page 10, line 33	1-14

☐ Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *Z* document member of the same patent family

Date of the actual completion of the international search

23 May 2003

Date of mailing of the international search report

02/06/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Vorweg, N

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/GB 03/00832

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6145979	A	14-11-2000	AU 6525396 A DE 69606644 D1 DE 69606644 T2 EP 0842051 A1 WO 9704964 A1	26-02-1997 16-03-2000 27-07-2000 20-05-1998 13-02-1997
WO 0030856	A	02-06-2000	AU 1282600 A CA 2348508 A1 EP 1131209 A1 WO 0030856 A1 JP 2002530229 T	13-06-2000 02-06-2000 12-09-2001 02-06-2000 17-09-2002
US 2001038408	A1	08-11-2001	US 6312123 B1 WO 02078958 A1 AU 6950100 A CN 1377313 T EP 1212195 A1 JP 2003508277 T WO 0117780 A1 US 2002005870 A1 US 2002044188 A1	06-11-2001 10-10-2002 10-04-2001 30-10-2002 12-06-2002 04-03-2003 15-03-2001 17-01-2002 18-04-2002
EP 0914875	A	12-05-1999	JP 11128831 A JP 11128832 A JP 11169784 A EP 0914875 A2 US 6231984 B1	18-05-1999 18-05-1999 29-06-1999 12-05-1999 15-05-2001